




9645 Airport Hwy,  
Monclova, OH 43542  
419-861-9600



## COBBLEFIELD CHARDONNAY 64 LINEAR FOOT BIG BOX

Designed to emulate the architecture of rural 19th-century America. Its rugged refinement makes it equally at home in residential or commercial settings. Dimensions (approx): 2" - 8" H x 4" - 20" L

**SKU** 9200

**Brand** CULTURED STONE

**Application/Use** Veneer

### Size

**Dimension** Corner Returns 3" - 12"

**Height** 2" - 8"

**Thickness** 1" - 2 5/8"

### Characteristics

**Color** Rust|Tan|Cream Brown

**Cut** Cobblefield

**Veneer Type** Thin Veneer

**Material** Concrete

### Data

**ASTM TESTING DATA** Materials cement Astm C 150 or Aci 318 Section 3.2.1 sand Astm C 144 or C 33 aggregate Astm C 33 or C 330 (except Gradation), C 331 testing shear Bond Test (adhesion) tested in Accordance With Astm C 482 > 50 Psi water Absorption Tested in Accordance With Ubc 15-5 9%-22% Depending on Texture freeze/thaw Characteristics testing Procedures Follow Those Outlined in Astm C 67 < 3% Mass Loss compressive Strength tested in Accordance With Astm C 39 > 1800 Psi @ 28 Days unit Weight density Is Determined in Accordance With Astm C 567 < 15 Lbs. Per Square Foot tensile Strength Tested in Accordance With Astm C 190 Reported flexural Strength Tested in Accordance With Astm C 348 Reported thermal Properties tested in Accordance With Astm C 177-71 r-value Is .620 Based on a 1.75" Thick Sample. Average Thickness May Vary on Different Cultured Stone Veneer Products, and the R-value Will Vary Accordingly. noncombustible tested and Listed by Underwriters Laboratories, Inc. cultured Stone Brand Products Showed Zero

Flame Spread and Zero Smoke Development.

---

**Coverage & Weight**

Coverage per Box 64 LIN FT

---