





FOND DU LAC HERITAGE BLEND FULL VENEER

The historic appearance of randomly layered stone is created using heights from 2" to 12" and lengths from 6" to 24" for both full and thin veneer stone. Its natural stone colors range from light grays to whites, browns, buffs, tans, and golds.

SKU 2300

Brand BUECHEL

Application/Use Veneer

Size

Length 6" - 24"

Height 2" - 12"

Thickness 3" - 5"

Characteristics

Cut Ashlar

Stone Type Dolomitic Limestone

Veneer Type Full

Data

ASTM TESTING DATA Fond Du Lac C97 Water Absorption-0.36% Fond Du Lac C97 Density-174.2 Pcf Fond Du Lac C99 Modulus of Rupture-1,470 Psi Fond Du Lac C170 Compressive Strength W/rift-29,040 Psi Compressive Strength Across Rift-34,240 Psi Fond Du Lac C880 Flexural Strength-1,740 Psi

Coverage & Weight