



9645 Airport Hwy,  
Monclova, OH 43542  
419-861-9600



## SCULPTED ASHLAR GROUSE 64 LINEAR FOOT BIG BOX

The modern touch on classic charm. Mixed stone sizes bring natural warmth to interiors and exteriors, while precise lines keep it an appropriate choice for sleeker spaces. Dimensions (approx): 2.25" - 7.57" H x 5.5" - 20.5" L

**SKU** 17059

**Brand** CULTURED STONE

**Application/Use** Veneer

### Size

**Dimension** Corner Returns 4", 7", 10"

**Height** 2.25" - 7.75"

**Thickness** 1" - 2"

### Characteristics

**Color** Tan|Light Gray|Cream

**Material** Concrete

**Veneer Type** Thin

### Data

**ASTM TESTING DATA** Materials Cement Astm C 150 or Aci 318 Section 3.2.1 Sand Astm C 144 or C 33 Aggregate Astm C 33 or C 330 (except Gradation), C 331 Testing Shear Bond Test (adhesion) Tested in Accordance With Astm C 482 > 50 Psi Water Absorption Tested in Accordance With Ubc 15-5 9%-22% Depending on Texture Freeze/thaw Characteristics Testing Procedures Follow Those Outlined in Astm C 67 < 3% Mass Loss Compressive Strength Tested in Accordance With Astm C 39 > 1800 Psi @ 28 Days Unit Weight Density Is Determined in Accordance With Astm C 567 < 15 Lbs. Per Square Foot Tensile Strength Tested in Accordance With Astm C 190 Reported Flexural Strength Tested in Accordance With Astm C 348 Reported Thermal Properties Tested in Accordance With Astm C 177-71 R-value Is .620 Based on a 1.75" Thick Sample. Average Thickness May Vary on Different Cultured Stone Veneer Products, and the R-value Will Vary Accordingly. Noncombustible Tested and Listed by Underwriters Laboratories, Inc. Cultured Stone Brand Products

Showed Zero Flame Spread and Zero Smoke Development.

---

**Coverage & Weight**

Coverage per Box 64 LIN FT

---