



**9645 Airport Hwy,
Monclova, OH 43542
419-861-9600**



SOUTHERN LEDGESTONE CHARDONNAY 8 LINEAR FOOT HANDIPACK

Offers a rugged and informal appeal with its rough texture and decided irregularity. Tight-fitted or mortared, can be used to achieve a number of unique treatments.
Dimensions (approx): 0.5" - 6" H x 4" - 20" L

SKU 7585

Brand CULTURED STONE

Application/Use Veneer

Size

Dimension Corner Returns 4-12"

Thickness 1- 2.625"

Height .5 - 6"

Characteristics

Color Cream, Red, Tan, Charcoal Gray

Veneer Type Thin

Material Concrete

Data

ASTM TESTING DATA Materials Cement Astm C 150 or Aci 318 Section 3.2.1 Sand Astm C 144 or C 33 Aggregate Astm C 33 or C 330 (except Gradation), C 331 Testing Shear Bond Test (adhesion) Tested in Accordance With Astm C 482 > 50 Psi Water Absorption Tested in Accordance With Ubc 15-5 9%-22% Depending on Texture Freeze/thaw Characteristics Testing Procedures Follow Those Outlined in Astm C 67 < 3% Mass Loss Compressive Strength Tested in Accordance With Astm C 39 > 1800 Psi @ 28 Days Unit Weight Density Is Determined in Accordance With Astm C 567 < 15 Lbs. Per Square Foot Tensile Strength Tested in Accordance With Astm C 190 Reported Flexural Strength Tested in Accordance With Astm C 348 Reported Thermal Properties Tested in Accordance With Astm C 177-71 R-value Is .620 Based on a 1.75" Thick Sample. Average Thickness May Vary on Different Cultured Stone Veneer Products, and the R-value Will Vary Accordingly. Noncombustible Tested and Listed by Underwriters Laboratories, Inc. Cultured Stone Brand Products Showed Zero Flame Spread and Zero Smoke Development.

Coverage & Weight

Coverage per Box 8 LIN FT

Lbs per Create 104

Lbs per sqft 13
