



9645 Airport Hwy,  
Monclova, OH 43542  
419-861-9600



## SOUTHERN LEDGESTONE GRAY 10.5 SQUARE FOOT HANDIPACK

Offers a rugged and informal appeal with its rough texture and decided irregularity. Tight-fitted or mortared, can be used to achieve a number of unique treatments.  
Dimensions (approx): 0.5" - 6" H x 4" - 20" L

**SKU** 9522

**Brand** CULTURED STONE

**Application/Use** Veneer

### Size

**Length** 4-20"

**Height** .5 - 6"

**Thickness** 1- 2.625"

### Characteristics

**Color** Charcoal Gray|Light Gray|Tan

**Material** Concrete

**Veneer Type** Thin

### Data

**ASTM TESTING DATA** Materials Cement Astm C 150 or Aci 318 Section 3.2.1 Sand Astm C 144 or C 33 Aggregate Astm C 33 or C 330 (except Gradation), C 331 Testing Shear Bond Test (adhesion) Tested in Accordance With Astm C 482 > 50 Psi Water Absorption Tested in Accordance With Ubc 15-5 9%-22% Depending on Texture Freeze/thaw Characteristics Testing Procedures Follow Those Outlined in Astm C 67 < 3% Mass Loss Compressive Strength Tested in Accordance With Astm C 39 > 1800 Psi @ 28 Days Unit Weight Density Is Determined in Accordance With Astm C 567 < 15 Lbs. Per Square Foot Tensile Strength Tested in Accordance With Astm C 190 Reported Flexural Strength Tested in Accordance With Astm C 348 Reported Thermal Properties Tested in Accordance With Astm C 177-71 R-value Is .620 Based on a 1.75" Thick Sample. Average Thickness May Vary on Different Cultured Stone Veneer Products, and the R-value Will Vary Accordingly. Noncombustible Tested and Listed by Underwriters Laboratories, Inc. Cultured Stone Brand Products

Showed Zero Flame Spread and Zero Smoke Development.

---

Coverage & Weight

Coverage per Box 10.5 SQ FT

---